

# PERMALINE

<b>Composition</b>	PVC
<b>Thickness</b>	1mm
<b>K-value</b>	67
<b>Hardness shore A</b>	SHORE (A)94
<b>Polymerization degree</b>	100+/-10
<b>PVC Resin</b>	100%
<b>DOP</b>	34%
<b>Epoxy Soybean oil</b>	2%
<b>Ca Za Stabilizer</b>	1.80%
<b>Lubricant</b>	0.80%
<b>Processing Aid</b>	1.30%
<b>Burning Resistance</b>	6.00%
<b>(Processing Aid) Q UV</b>	0.50%
<b>Processing Aid</b>	1.30%

<b>Adhesive Base</b>	
<b>Backing Material</b>	PET 0.025mm
<b>Thickness</b>	0.22+/- 0.015
<b>Initial Tack (cm) PSTC-6</b>	< 8
<b>180 degree Adhesion (kg / inch) ASTM-D1000</b>	> 1.8
<b>Holding Power (hrs/kg/in2 PSTC-7</b>	> 48
<b>80 degrees C/0.5kg (hrs/inch2)</b>	> 24

All data is for reference only, users should perform their own tests to determine suitability.



**EDSON**  
ELECTRONICS

incorporating  
**firstsolutiononline**  
one stop for all your premises solutions